

AMENDMENTS TO THE CLAIMS

1. (Previously Presented) A method comprising:
expanding a graphite material from a first density to a smaller second density; and
following expansion, purifying the graphite material at a temperature of at least 1750°C.
2. (Original) The method of claim 1, wherein the graphite material comprises a natural graphite flake.
3. (Original) The method of claim 1, wherein expanding a graphite material comprises:
combining the graphite material with an intercalating agent.
4. (Original) The method of claim 3, wherein the intercalating agent is nitric acid.
5. (Original) The method of claim 4, wherein expanding the graphite material comprises:
combining the graphite material and the intercalating agent at a graphite material to intercalating agent at a ratio of about three to one.
6. (Original) The method of claim 3, wherein expanding the graphite material comprises, after combining the graphite material with the intercalating agent, subjecting the graphite material to a thermal treatment.
7. (Original) The method of claim 6, further comprising:
prior to purifying, compacting the graphite material.
8. (Previously Presented) The method of claim 6, wherein the thermal treatment comprises a first thermal treatment and purifying the graphite comprises subjecting the

graphite material to a second thermal treatment under vacuum at a temperature in the range of 1750 to 3000°C.

9. (Original) The method of claim 8, wherein subjecting the graphic material to a second thermal treatment further comprises introducing an auxiliary gas into the vacuum environment.

10. (Original) The method of claim 9, wherein the auxiliary gas comprises chlorine.

11. (Original) The method of claim 1, further comprising:
following purifying, one of grinding and compacting the graphite material.

12. (Original) The method of claim 1, further comprising:
following purifying, compacting the graphite material; and
following compacting, grinding the graphite material.

13. (Previously Presented) A method comprising:
expanding a graphite material;
following expansion, compacting the graphite material; and
following compaction, purifying the graphite material at a temperature of at least 1750°C.

14. (Original) The method of claim 13, wherein expanding a graphite material comprises:

combining the graphite material with an intercalating agent.

15. (Original) The method of claim 14, wherein the intercalating agent is nitric acid.

16. (Original) The method of claim 15, wherein expanding the graphite material comprises:

combining the graphite material and the intercalating agent at a graphite material to intercalating ratio of about three to one.

17. (Currently Amended) The method of claim ~~13~~ 14, wherein expanding the graphite material comprises, after combining the graphite material with the intercalating agent, subjecting the graphite material to a first thermal treatment.

18. (Previously Presented) The method of claim 17, wherein purifying the graphite material comprises a second thermal treatment and the second thermal treatment comprises purifying under vacuum at a temperature in the range of 1750 to 3000°C.

19. (Original) The method of claim 17, wherein subjecting the graphic material to a second thermal treatment further comprises introducing an auxiliary gas into the vacuum environment.

20. (Original) The method of claim 19, wherein the auxiliary gas comprises chlorine.

21. (Original) The method of claim 13, further comprising:

following purifying, one of grinding and compacting the graphite material.

22. (Original) The method of claim 13, further comprising:

following purifying, compacting the graphite material; and

following compacting, grinding the graphite material.

23. (Original) The method of claim 13, wherein the graphite material comprises a natural graphite flake.

24. (Previously Presented) An article of manufacture comprising graphite formed according to a method comprising:

expanding a graphite material from a first density to a smaller second density; and following expansion, purifying the graphite material at a temperature of at least 1750°C.

25. (Original) The article of manufacture of claim 24, wherein expanding a graphite material comprises:

combining the graphite material with an intercalating agent.

26. (Original) The article of manufacture of claim 25, wherein the intercalating agent is nitric acid.

27. (Original) The article of manufacture of claim 24, wherein the graphite material comprises a natural graphite flake.

Respectfully submitted,

BLAKELY SOKOLOFF TAYLOR & ZAFMAN LLP

Dated: 9/18/2003




Farzad E. Amini, Reg. No. 42,261

12400 Wilshire Boulevard
Seventh Floor
Los Angeles, California 90025
(310) 207-3800

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail with sufficient postage in an envelope addressed to: Mail Stop Appeal Brief-Patents, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450 on September 18, 2003.



Nadya Gordon

9/18/03
Date